


COPAL OGL 2



Grease



Extreme pressure adhesive aluminium complex grease with solid lubricants for heavy-duty applications.

APPLICATIONS

**Heavy duty grease,
water resistant**

Recommendation

- ⌘ **COPAL OGL 2** is a predominantly designed for use on open gears, in case where an NLGI 2grade is required.
- ⌘ **COPAL OGL 2** can be used as a priming lubricant for gears of kilns, mills,...
- ⌘ **COPAL OGL 2** can be used as well in plain bearings highly loaded in the most severe conditions. (shocks,high loads, high amount of water,...) or for application requiring a highly adhesive grease (fifth wheel,...).
- ⌘ Preferably use a pneumatic pump system. **COPAL OGL 2** can be applied by hand with brushes, or other adapted tools. A good cleanliness of tools is recommended for optimal lubrication.

SPECIFICATIONS

- ⌘ ISO 6743-9: L-XBDEB 2
- ⌘ DIN 51502: OGP2N-15

ADVANTAGES

**High load resistance
High adhesiveness**

**Water resistance
No harmful substance**

- ⌘ Excellent adhesiveness, associated with the very good resistance to high loads and repeated shock loadings, **COPAL OGL 2**, gives a high protection level against wear on gear teeth and plain bearings, increasing significantly the service life of the equipment.
- ⌘ **COPAL OGL 2** contains solid lubricants, decreasing friction coefficient, limiting wear particularly near the tooth crest and tooth base, decreasing energy consumption.
- ⌘ Good behaviour in presence of water even under pressure.
- ⌘ **COPAL OGL 2** does not contain lead, or other heavy metals considered harmful to human health and the environment.

CHARACTERISTICS	METHODS	UNITS	COPAL OGL 2
Soap/thickener		-	Aluminium complex 2
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Anthracite
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 15 to 150
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265-295
Four ball weld load	ASTM D2596	kg	> 800
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0-0
Dropping point	IP 396/DIN ISO 2176	°C	> 245
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm ² /s (cSt)	> 1000

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS
Industrie & Spécialités
11-09-2006
COPAL OGL 2
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.